



# Kkalpana Industries (India) Limited

<b>GRADE</b>	<b>KALPLENE PP2T</b>
<b>FEATURE</b>	<b>PP TALC FILLED 25 %</b>
<b>PRESENTATION</b>	<b>PRE COLOURED /NATURAL / BLACK</b>

## TECHNICAL DATA SHEET

<b>PROPERTIES</b>	<b>ASTM TEST METHOD</b>	<b>TEST CONDITION</b>	<b>UNIT</b>	<b>KALPLENE PP2T COLOR XXXX (VALUE)</b>
<b><u>PHYSICAL PROPERTIES</u> at 23 °C</b>				
Melt Flow Rate	D-1238	230°C/2.16kg	gm/10 min	14 ± 01
Specific Gravity*	D-792		-	1.12±0.02
<b><u>THERMAL PROPERTIES</u></b>				
Heat Deflection Temperature* 12.7mm x 6.4mm x 127mm Bar	D-648	18.56 Kg/cm <sup>2</sup>  Annealed at 110 Deg C/2 Hr	°C	115 ± 5
<b><u>FLAMMABILITY</u></b>	UL-94			HB
<b><u>MECHANICAL PROPERTIES</u></b>				
Notched Izod Impact Strength	D-256	3.2mm at 23 <sup>o</sup> C	Kgfc/cm	4.0 ± 1
Tensile Strength at yield	D-638	50 mm/min	Kg/cm <sup>2</sup>	235 ± 20
Flexural Modulus*	D-790	5 mm/min	Kg/cm <sup>2</sup>	25000 ± 1000

To be measured as & when necessary  
It is necessary to pre-dry material at 85°C for 2 to 3 hours prior to processing.  
Inj Mold Condition – 170 -190 °C

### DISCLAIMER:

The above Technical Data Sheet presents information and data, true and accurate to the best of our knowledge.

No warranty express or implied can be made regarding performance or otherwise.

(As this is computer generated, no signature is required)

**Surangi Works** : Survey No. - 320/1/1/2/2, Village – Surangi, Chikhali Road, Silvassa – 396240 (Dadra & Nagar Haveli), Tel : 0260-2406400, Mob : +91 9909006402, E-mail : surangi@kkalpana.co.in

**Dadra Works** : Survey No – 24/3, Village : Demni, Demni Road, Dadra, Silvassa - 396193 (Dadra & Nagar Haveli) Tel: 0260-6544484, Mob : +91 9909006426, Fax No. : 0260-2668760, E-mail : dadra@kkalpana.co.in

**Daman Works** : 168/151-158, Dabhel Industrial Co-operative Society Ltd., Dabhel, Daman - 396210 Tel: +91-0260-2242682 / 2241994, Fax : +91-0260-2243799, E-mail : daman@kkalpana.co.in

www.kkalpanagroup.com

CIN : L19202WB1985PLC039431