



Kkalpana Industries (India) Limited

An ISO 9001:2015 company
TECHNICAL DATA

Silane Grafted XLPE Compound for Aerial Bunch Cable:

KI – XL - 03 / XL - 04 / XL - ABC

DESCRIPTION:

A Low Density Cross Linkable Polyethylene compound consisting of 3 Components i.e. Grafted Polymer – Grade KI-XL-03, Catalyst Master Batch KI-XL-04 a specially designed Master Batch, KI-XL-ABC packed separately. The components are to be mixed in ratio of 90:5:5 parts just before consumption.

Such system allows the compound to be extruded as a normal thermoplastic in a conventional PE (or even PVC) extrusion line. The cross-linking step is subsequently carried out by immersion in hot water, or exposure to steam. In each case, time of curing is to be optimized as a function of thickness of insulation, concentration of catalyst and temperature. The formulation ensures delivery of requisite amount of carbon black in finished cable.

SPECIFICATIONS:

KI-XL 03 / XL 04 / XL ABC combination meets requirements as applicable under following standards, when processed using sound extrusion practice and testing procedure;

- IS-7098 Part 1 / IS 10810
- BS 5467, 5468, 6724, 7655
- IEC 60502

TYPICAL PROPERTIES:

A) XL-03

Property	Unit	Typical Value	Test Method
Density	gm /cm ³	0.923 – 0.925	ASTM-D-792
Melt Flow Index (190°C, 2.16 Kg)	gm / 10 Min	0.6 – 2.0	IS-10810 (Part-23) / ASTM-D-1238
Contamination	No./Kg	< 5	KIIL

MKT: TDS – 03/04/ABC – 11/17

B) XL-03 / XL-04 / XL-ABC Combination

Mixed at 130°C at 90:5:5 parts for 3 minutes, compression mould to a sheet of 1.5 mm thickness cured by immersion in water at 95°C for 3 hrs; conditioning for 3 hrs.

Property	Unit	Typical Value	Test Method
Tensile Strength	MPa	16 - 19	IS-10810 Part-7 / ASTM-D-638
Elongation at break	%	500 – 600	IS-10810 Part-7 / ASTM-D-638
Hot set at 200 °C			
a) Hot Elongation after 15 min.	%	60 – 90	IS-10810 Part-30 / IEC 60811-507
b) Permanent Set after after 5 min	%	± 5	-- do --
Oven ageing at 135 °C, 168 hours			
a) Variation in Tensile Strength	%	± 15	IS-10810 Part-11 / IEC 60811-401
b) Variation in Elongation at Break	%	± 15	IS-10810 Part-11 / IEC 60811-401
Volume Resistivity @ 25°C	Ohm-cm	1 X 10 ¹⁵	ASTM –D-257
Dissipation factor @ 250V / 50 Hz, 25°C	-	0.007	ASTM-D-150
Dielectric Constant @ 250V / 50Hz, 25°C	-	2.6	ASTM-D-150

PROCESSING GUIDELINES :

It is recommended to dry the Catalyst Master Batch at 60°C in air oven in 4-6 cm layers for 8–12 hours. The Grafted Polymer should never be pre-heated.

The Grafted Polymer, Catalyst Mater Batch and special additive should be manually mixed at a ratio 90:5:5 at room temperature, just before consumption. Mixing in large quantities should be avoided, since such leftover premix cannot be stored.

It is important that the extruder should not be kept idle for more than 10 minutes when filled with XL 03 / XL 04 premix. It should be kept running at Low RPM if it is desired to change over size of conductor etc.

MKT: TDS – 03/04/ABC – 11/17

PACKAGING:

- Moisture Barrier Multilayer Bags of 25 kg.
- 20' FCL will take palletized 11 MT. & 40' FCL will take 24.75 MT.

STORAGE:

The shelf life of the product is 90 days (In case of Export packaging the shelf life is guaranteed for 180 days instead of 90 days) from the date of production, subject to following conditions:

- Storage temperature not generally exceeding 25°C.
- Away from direct sunlight and weathering.
- Closed and unbroken bags.
- Use of compound within 3-4 hours after bags are open.

The information given in the document is believed to be reliable and is given in the good faith but without warranty. The user should test the product to ascertain the suitability for the intended use. Product specification or the whole document is subject to change without any prior notice.

MKT: TDS – 03/04/ABC – 11/17